



TROPICAL HARDWOOD - SAWN TIMBER



TROPICAL HARDWOOD FROM MULTIPLE ORIGINS

- * Africa
- * Asia
- * South America

WIDE RANGE OF SPECIES AND SIZES

LEGALITY

- * Full compliance with the European Timber Regulation (EUTR)

ECOLOGY

- * PEFC, FSC® certificate available



Het keurmerk voor verantwoord bosbeheer





TROPICAL HARDWOOD SAWN TIMBER



Content

African hardwood

Afrormosia	p4
Ayous	p4
Beli	p4
Bilinga	p4
Bosse	p5
Doussie	p5
Eveuss	p5
Frake	p5
Gombe	p5
Iroko	p6
Kotibe	p6
Moabi	p6
Movingui	p6
Mukulungu	p6
Niove	p7
Ovengkol	p7
Padouk	p7
Sipo	p7
Tali	p7
Wengé	p8



TROPICAL HARDWOOD SAWN TIMBER



Asian hardwood

Geronggang	p9
Kapur	p9
Kempas	p9
Keruing	p9
Mahogany	p10
Melunak	p10
Mengkulang	p10
Meranti - Dark Red Meranti - Bukit	p10
Meranti - Dark Red Meranti - DUC	p10
Meranti - Dark Red Meranti - Nemesu	p11
Meranti - Dark Red Meranti- Seraya	p11
Meranti - Dark Red Meranti - Seraya Majau	p11
Meranti - Gerutu	p11
Meranti - Urat Mata	p11
Merbau	p12
Palissander - Rosewood	p12
Selangan Batu - Bangkirai	p12
Teak	p12

Soud-American hardwood

Cumaru	p13
Faveira Amargosa	p13
Garapa	p13
Ipe	p13
Jatoba	p14
Massaranduba	p14
Pequia	p14
Sucupira	p14
Tatajuba	p14



TROPICAL HARDWOOD SAWN TIMBER



African hardwood

AFRORMOSIA (Periscopsis E/M)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 % / CITES
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 750 kg/m ³

AYOUS (Triplochiton scleroxylon K. Schum.)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR
<u>Drying process</u>	KD
<u>Durability</u>	Class V
<u>Density</u>	± 390 kg/m ³

BELI (Julbernardia pellegriniana)



<u>Origin</u>	Cameroon, Gabon
<u>Certification</u>	EUTR
<u>Drying process</u>	KD
<u>Durability</u>	Class III
<u>Density</u>	± 770 kg/m ³

BILINGA (Nauclea diderrichii)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 750 kg/m ³

BOSSE (Guarea cedrata)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class II
<u>Density</u>	± 770 kg/m ³

DOUSSIE (Afzelia bipindensis)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 800 kg/m ³

EVEUSS (Klainedoxa gabonensis)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 1050 kg/m ³

FRAKE (Terminalia superba)



<u>Origin</u>	Cameroon, Gabon
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class IV
<u>Density</u>	± 550 kg/m ³

GOMBE (Didelotia africana)



<u>Origin</u>	Cameroon, Gabon
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class IV
<u>Density</u>	± 650 kg/m ³

IROKO (*Milicia excelsa*)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I-II
<u>Density</u>	± 650 kg/m ³

KOTIBE (*Nesogordonia papaverifera*)




<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class III
<u>Density</u>	± 760 kg/m ³

MOABI (*Baillonella toxisperma*)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 880 kg/m ³

MOVINGUI (*Distemonanthus benthamianus*)



<u>Origin</u>	Cameroon, Gabon
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class III
<u>Density</u>	± 730 kg/m ³

MUKULUNGU (*Autranella congolensis*)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 950 kg/m ³

NIOVE (*Staudtia stipitata*)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 880 kg/m ³

OVENGKOL (*Guibourtia ehie*)



<u>Origin</u>	Cameroon, Gabon
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class II
<u>Density</u>	± 800 kg/m ³

PADOUK (*Pterocarpus soyauxii*)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 790 kg/m ³

SIPO (*Entandrophragma utile*)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class II-III
<u>Density</u>	± 630 kg/m ³

TALI (*Erythrophleum ivorense*)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 900 kg/m ³



TROPICAL HARDWOOD SAWN TIMBER



WENGE (Millettia stuhlmannii)



<u>Origin</u>	Cameroon, Gabon, DRC
<u>Certification</u>	EUTR
<u>Drying process</u>	KD
<u>Durability</u>	Class II
<u>Density</u>	± 870 kg/m ³





TROPICAL HARDWOOD SAWN TIMBER



Asian hardwood

GERONGGANG (*Cratoxylum arborescens*)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / 100 % PEFC certified
<u>Drying process</u>	KD
<u>Durability</u>	Class V
<u>Density</u>	± 450 kg/m ³

KAPUR (*Dryobalanops* spp.)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / FSC 100 % / 100 % PEFC certified
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I-II
<u>Density</u>	± 750 kg/m ³

KEMPAS (*Koompassia malaccensis*)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class II
<u>Density</u>	± 875 kg/m ³

KERUING (*Dipterocarpus* spp.)




<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / FSC 100 % / 100 % PEFC certified
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class III
<u>Density</u>	± 800 kg/m ³

MAHOGANY (Swietenia macrophylla King Acajou/Mongo)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class II
<u>Density</u>	± 540 kg/m ³

MELUNAK (Pentace spp.)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / 100 % PEFC certified
<u>Drying process</u>	KD
<u>Durability</u>	Class III
<u>Density</u>	± 640 kg/m ³

MENKULANG (Tarrietia javanica)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / 100 % PEFC certified
<u>Drying process</u>	KD
<u>Durability</u>	Class IV
<u>Density</u>	± 680 kg/m ³

MERANTI - DARK RED MERANTI - BUKIT



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / 100 % PEFC certified
<u>Drying process</u>	KD
<u>Durability</u>	Class II
<u>Density</u>	± 750 kg/m ³

MERANTI - DARK RED MERANTI - DUC



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD
<u>Durability</u>	Class III-IV
<u>Density</u>	± 480 kg/m ³

MERANTI - DARK RED MERANTI - NEMESU (*Shorea pauciflora*)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / 100 % PEFC certified
<u>Drying process</u>	KD
<u>Durability</u>	Class II
<u>Density</u>	± 650 kg/m ³

MERANTI - DARK RED MERANTI - SERAYA



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / FSC 100 % / 100 % PEFC certified
<u>Drying process</u>	KD
<u>Durability</u>	Class III
<u>Density</u>	± 500 kg/m ³

MERANTI - DARK RED MERANTI - SERAYA MAJAU (*Shorea spp.*)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / FSC 100 % / 100 % PEFC certified
<u>Drying process</u>	KD
<u>Durability</u>	Class III
<u>Density</u>	± 500 kg/m ³

MERANTI - GERUTU - (*Parashorea*)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / 100 % PEFC certified
<u>Drying process</u>	KD
<u>Durability</u>	Class III
<u>Density</u>	± 750 kg/m ³

MERANTI - URAT MATA



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD
<u>Durability</u>	Class III-IV
<u>Density</u>	± 650 kg/m ³



TROPICAL HARDWOOD SAWN TIMBER



MERBAU (Intsia bijuga)



<u>Origin</u>	Indonesia, Malaysia
<u>Certification</u>	EUTR / FSC 100 % / 100 % PEFC certified
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I-II
<u>Density</u>	± 820 kg/m ³

PALISSANDER - ROSEWOOD



<u>Origin</u>	Indonesia
<u>Certification</u>	EUTR / Cites
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 975 kg/m ³

SELANGAN BATU - BANGKIRAI



<u>Origin</u>	Indonesia
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class II
<u>Density</u>	± 930 kg/m ³

TEAK (Tectona grandis)



<u>Origin</u>	Indonesia, Myanmar
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 650 kg/m ³

South-American hardwood

CUMARU (*Dipteryx* spp.)



<u>Origin</u>	Brazil, Bolivia
<u>Certification</u>	EUTR
<u>Drying process</u>	KD
<u>Durability</u>	Class I
<u>Density</u>	± 1070 kg/m ³

FAVEIRA AMARGOSA (*Vatairea guianensis*)



<u>Origin</u>	Brazil
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 775 kg/m ³

GARAPA (*Apuleia leiocarpa*)



<u>Origin</u>	Brazil, Bolivia
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class III
<u>Density</u>	± 800 kg/m ³

IPE (*Tabebuia* spp.)



<u>Origin</u>	Brazil, Bolivia
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 1040 kg/m ³

JATOBA (*Hymenaea courbaril*)



<u>Origin</u>	Brazil
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class II-III
<u>Density</u>	± 1000 kg/m ³

MASSARANDUBA (*Manilkara bidentata*)



<u>Origin</u>	Brazil
<u>Certification</u>	EUTR / FSC 100 %
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 1100 kg/m ³

PIQUIÁ (*Caryocar glabrum*)



<u>Origin</u>	Brazil
<u>Certification</u>	EUTR
<u>Drying process</u>	AD
<u>Durability</u>	Class I
<u>Density</u>	± 800 kg/m ³

SUCUPIRA (*Bowdichia nitida*)



<u>Origin</u>	Brazil
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class II
<u>Density</u>	± 920 kg/m ³

TATAJUBA (*Bagassa guianensis*)



<u>Origin</u>	Brazil
<u>Certification</u>	EUTR
<u>Drying process</u>	KD / AD
<u>Durability</u>	Class I
<u>Density</u>	± 800 kg/m ³